

PRODUCT NAME :	KANSAI PLC 66 AC
DESCRIPTION :	<i>KANSAI PLC 66 AC is a pastel colored solvent-based coating designed for usage over damp surface. It bonds well to damp surface and allows the moisture to breathe through the coating film without damaging the coating.</i>
RECOMMENDED USE :	<i>KANSAI PLC 66 AC is recommended for old interior and exterior concrete or brick walls with continuous seepage of dampness such as exterior of shower wall and basement walls.</i>
PERFORMANCE :	<ul style="list-style-type: none">• <i>Excellent alkali resistance.</i>• <i>Highly breathable</i>• <i>Excellent adhesion to damp surfaces</i>• <i>Easy application - simple application procedures</i>
PHYSICAL PROPERTIES	
COLOUR	<i>Pastel colors</i>
NO. OF COMPONENTS	<i>One</i>
VOLUME SOLIDS	<i>40 %</i>
RECOMMENDED THICKNESS	<i>50 microns DFT per coat</i>
TEORETICAL COVERAGE	<i>8 m²/liter @ 50 microns DFT</i>
NO. OF COATS	<i>One</i>
RECOMMENDED DRYING TIME	<i>Touch dry : 45 minutes</i> <i>Top coat: 5 hours.</i>
PACKING SIZE	<i>5 liters and 20 liters.</i>
SURFACE PREPARATION	<i>Surface to be coated must be dry and free form oil and grease, chalked and deteriorated materials shall be removed by scrapping or water.</i>
APPLICATION	<i>KANSAI PLC 66 AC can be applied by roller, brush or spray. For roller application, use only recommended thinner to ensure good workability.</i>
DRYING	<i>Allow to dry for at least 5 hours before top-coating.</i>
CLEANING	<i>Clean all tools and equipment with KANSAI PLC Cleaner #72 immediately after use.</i>

For further information on Product Data, please contact:

Protective Coatings Sales Department

Kansai Paint Asia Pacific Sdn Bhd. (705919-W)
4 Solok Waja 2, Kawasan Perindustrian Bukit Raja, P.O.BOX 159, 41710 Klang, Selangor, Malaysia
Tel: 6(03) 3362 2388 Fax: 6(03) 3342 7223

DISCLAIMER :

The information in this sheet is provided to the best of our knowledge based on laboratory testing and practical experience. However, as the product is often used under conditions beyond the manufacturer's control, it is the sole responsibility of the buyer to obtain confirmation from the manufacturer on the suitability of the product for the intended use. Therefore, the manufacturer can accept no liability for the performance of the product, or any loss or damage arising out of such use. The information detailed in this data sheet is subject to change without notice in light of experience and of normal product development.

Date Issued: November 2016
Revision No: 0

Page 1 of 1

This Technical Data Sheet supersedes those previously issued.