

PRODUCT NAME :	KANSAI PLC 83 AC
DESCRIPTION :	<i>KANSAI PLC 83 AC is a clear solvent-based acrylic sealer designed for usage as an alkaline resistance primer for architectural finishes.</i>
RECOMMENDED USE :	<i>KANSAI PLC 83 AC is recommended for old and new interior and exterior walls. It is suitable for substrates made of cement, concrete, clay and cement bricks, GRC board and etc. where high penetration and alkaline resistant primer is required.</i>
PERFORMANCE :	<ul style="list-style-type: none"> • <i>Excellent alkali resistance.</i> • <i>Adhesion - Excellent adhesion over painted surfaces.</i> • <i>Easy application - simple application procedures.</i> • <i>Excellent weathering resistance for exterior applications.</i>
PHYSICAL PROPERTIES	
COLOUR	<i>Translucent clear</i>
NO. OF COMPONENTS	<i>One</i>
VOLUME SOLIDS	<i>32 %</i>
RECOMMENDED THICKNESS	<i>40 microns DFT per coat</i>
TEORETICAL COVERAGE	<i>8 m²/liter @ 40 microns DFT.</i>
NO. OF COATS	<i>One</i>
RECOMMENDED DRYING TIME	<i>Touch dry : 30 minutes</i> <i>Topcoat: 2 hours.</i>
PACKING SIZE	<i>Packing Size : 20 liters</i>
THINNER	<i>KANSAI PLC Thinner #73</i>
SURFACE PREPARATION	<i>Surface to be coated must be dry and free from oil and grease.</i>
APPLICATION	<i>KANSAI PLC 83 AC can be applied by roller, brush or spray. For roller application, use only recommended thinner to ensure good workability.</i>
DRYING	<i>Allow to dry for at least 2 hours before top-coating.</i>
CLEANING	<i>Clean all tools and equipment with KANSAI PLC Cleaner #72 immediately after use.</i>

For further information on Product Data, please contact:

Protective Coatings Sales Department

Kansai Paint Asia Pacific Sdn Bhd. (705919-W)
4 Solok Waja 2, Kawasan Perindustrian Bukit Raja, P.O.BOX 159, 41710 Klang, Selangor, Malaysia
Tel: 6(03) 3362 2388 Fax: 6(03) 3342 7223

DISCLAIMER :

The information in this sheet is provided to the best of our knowledge based on laboratory testing and practical experience. However, as the product is often used under conditions beyond the manufacturer's control, it is the sole responsibility of the buyer to obtain confirmation from the manufacturer on the suitability of the product for the intended use. Therefore, the manufacturer can accept no liability for the performance of the product, or any loss or damage arising out of such use. The information detailed in this data sheet is subject to change without notice in light of experience and of normal product development.